#### (19) World Intellectual Property Organization International Bureau



## 

(43) International Publication Date 2 June 2005 (02.06.2005)

PCT

### (10) International Publication Number WO 2005/049664 A1

(51) International Patent Classification7:

C08F 10/02

(21) International Application Number:

PCT/EP2004/012108

(22) International Filing Date: 27 October 2004 (27.10.2004)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:

103 51 262.4 60/525,268

31 October 2003 (31.10.2003) 25 November 2003 (25.11.2003)

(71) Applicant (for all designated States except US): BASELL POLYOLEFINE GMBH [DE/DE]; Brühler Strasse 60. 50389 Wesseling (DE).

(72) Inventors; and

(75) Inventors/Applicants (for US only): GONIOUKH, Andrei [RU/DE]; Am Kapellenbusch 15, 50374 Erftstadt-Liblar (DE). KÖHLER, Gernot [DE/DE]; Johann-Sebastian-Bach Weg 3, 53340 Meckenheim (DE). TEUBER, Theo [DE/DE]; Maarweg 46, 50374 Erftstadt

(DE). DRÖGE, Thomas [DE/DE]; Maconring 98a, 67434 Neustsdt a. d. W. (DE).


- (81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM,
- (84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Declaration under Rule 4.17:

of inventorship (Rule 4.17(iv)) for US only

[Continued on next page]

(54) Title: CONTINUOUS PREPARATION OF ETHYLENE HOMOPOLYMERS OR COPOLYMERS



(57) Abstract: The invention relates to a process for the continuous preparation of ethylene homopolymers or copolymers in the presence of free-radical polymerization initiators and, if desired, molecular weight regulators at from 120°C to 350°C and pressures in the range from 100 to 4000 bar, in which the polymer is separated from unpolymerized ethylene in a high-pressure stage at a pressure of from 100 to 500 bar and at least one low-pressure stage at a pressure of from 1 to 100 bar and the ethylene separated off in the high-pressure stage is separated from remaining monomeric, oligomeric and/or polymeric constituents and recirculated to the inlet of the tube reactor in a high-pressure circuit and the ethylene separated off in the low-pressure stage is separated from remaining monomeric, oligomeric and/or polymeric constituents and recirculated to the inlet of the tube reactor in a low-pressure circuit. The initiator is used as a solution in an isoparaffinic solvent having a boiling point of not more than 160°C and the solvent is separated from the other monomeric, oligomeric and/or polymeric constituents in the low-pressure circuit. The solvent is then, if appropriate after being admixed with fresh solvent, reused for dissolving initiator.

# WO 2005/049664 A1

### Published:

with international search report

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.